TEST REPORT

To,
Titan Company Limited
Eye ware Division
Chickkaballapura,
Karnataka-562101

TEST RESULTS OF PAVER BLOCK (195X155X45MM)

Crushing Strength Test

Sl.no	Crushing load in KN	Compressive strength in N/mm²	Average Compressive strength in N/mm²
1	564	21.52	**21.75**
2	578	22.06	
3	568	21.67	

Note: Test Results Based on the Samples Delivered By Client to Our Laboratory